

検査表 INSPECTION REPORT

発行日: 2022/06/30
Issued Date:

需要家名: STANFORD LINEAR ACCELERATOR CENTER
Customer:

品名: N39UH 品名コード: 300000 図面No.: 2008002634
Material: Our Code No: Our Dwg. No:

需要家注文No.: 218764 需要家図面No.: PF-380-326-49
Customer's P/O No.: Customer's Dwg. No.:

指図No.: 7203438501-01 ケースNo.: 数量: 5
Our P/O No.: Carton No.: Quantity:

単位重量: 81.2 g/pc 磁化方向: T 着磁有無: MAGNETIZED
Unit Weight: Magnetization Through: Magnetization:

極表示:
Marking:

寸法: Dimension: 60.000 L 27.000 W 7.030 T

磁気特性: Magnetic Properties:

Br	[T]	1.244
	[G]	12442
Hcj	[kA/m]	2121
	[Oe]	26644
Hcb	[kA/m]	969
	[Oe]	12175
(BH) max	[kJ/m ³]	301.7
	[MGOe]	37.9

その他特性: Additinal Specification:

備考: Notes:

営業担当: Sales: Y. Kasagi

総合判定: Judgment:

承認: Approved by:

担当: Checked by:

PASSED

H. Fulcnoka

S. Iida

信越化学工業株式会社 Shin-Etsu Chemical Co.,Ltd



本社 電子材料事業本部:〒100-0004 東京都千代田区大手町2-6-1
マグネット部.....TEL:(03)3246-5246 FAX:(03)3246-5367

武生工場:〒915-8515 福井県越前市北府2-1-5
品質保証部.....TEL:(0778)21-8116 FAX:(0778)21-8134

HQ Electronics Materials Division:6-1,Ohtemachi 2-chome,Chiyoda-ku,Tokyo,Japan
Magnet Department.....TEL:+81-3-3246-5246 FAX:+81-3-3246-5367

Takefu Plant:1-5,Kitago 2-chome,Echizen-shi,Fukui,Japan
Q.A.Department.....TEL:+81-3-778-21-8116 FAX:+81-778-21-8134

Packing List

Date: 30-Jun-22

1	Forwarder: YUSEN LOGISTICS CO., LTD.			Shin-Etsu P/O No. : 7203438501-01		
	Customer : STANFORD LINEAR ACCELERATOR CENTER		Customer's P/O No. : 218764	Customer's Dwg/Part No. : PF-380-326-49		
	Shin-Etsu Code No. : 300000		Quantity: 5	Unit Weight: 81.2000 g/pc		
	Material : N39UH		Magnetization: MAGNETIZED	Note:		
	Details Of Packing		Carton No.	Quantity	Net Weight	Gross Weight
1 - 1			5	0.406	1.100	41.0 x 31.0 x 15.5
Total			5	0.406	1.100	

Shin-Etsu code : FD43851

magnetization direction measured by Helmholtz coil

MEASURER *S. Terachi*
 APRD. *H. Fukuda*

#	Magnetization [T]					Orientation [deg]		
	serial No.	Mx	My	Mz	M	dev-M [%]	T(Mx/Mz)	T(My/Mz)
501	-0.00653	0.00261	1.22935	1.22937	-0.082	-0.304	0.122	0.328
502	0.00131	-0.00261	1.23066	1.23066	0.022	0.061	-0.122	0.136
503	-0.00522	0.00131	1.23066	1.23067	0.023	-0.243	0.061	0.251
504	-0.02217	0.00261	1.22979	1.23000	-0.032	-1.033	0.122	1.040
505	0.00522	0.00000	1.23122	1.23123	0.069	0.243	0.000	0.243
Samples	5	5	5	5	5	5	5	5
Minimum	-0.02217	-0.00261	1.22935	1.22937	-0.08242	-1.03279	-0.12152	0.13586
Maximum	0.00522	0.00261	1.23122	1.23123	0.06881	0.24278	0.12165	1.03992
Range	0.02739	0.00522	0.00187	0.00186	0.15123	1.27557	0.24316	0.90406
Average	-0.00548	0.00078	1.23034	1.23039	0.00000	-0.25528	0.03648	0.39932
Std. Dev.	0.01049	0.00218	0.00075	0.00072	0.05821	0.48862	0.10170	0.36455

